

**Taizhou Huali Plastic Co. Ltd.**  
**Zhangdian Industrial Zone, Jiangyan District**  
**Jiangsu Province**  
**TAIZHOU CITY**  
**China**

**Your notice of**  
03-10-2017

**Your reference**

**Date**  
03-11-2017

**Analysis Report 17.05655.01**

Required tests :

**EN 13893 (2003)**

**Determination of the dynamic coefficient of friction of floor coverings**


Identification number	Information given by the client	Date of receipt
T1720952	Rigid Vinyl Plank with Silence Pad	03-10-2017

Kristina De Temmerman

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be**  
Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947  
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be  
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be  
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be  
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



**Reference: T1720952r - Rigid Vinyl Plank with Silence Pad**

**Determination of the dynamic coefficient of friction of floor coverings**

Date of ending the test 04-10-2017  
Standard used EN 13893 (2003)  
Conditioning 20°C, relative humidity 65%  
Apparatus GMG 200  
Number of test specimens 1  
Number of measurements 3 x Production  
3 x Non-production

Measurement	$\mu$ = dynamic coefficient of friction	
	Production direction	Non-production direction
1	0.52	0.55
2	0.55	0.55
3	0.55	0.55
Average	0.54	0.55